

Description:	Synergetic blend of organic and inorganic compounds.
Aspect:	White to beige thin powder.
Concentration:	Min. 88%
pH (sol. 10%):	6,0 – 8,0
Charge:	Anionic.
Application:	Retanning.
Properties:	<p>UNIPEL® EB has a filling effect in chrome leather. It gives the grain a more regular appearance and a fine break. With UNIPEL® EB loose grain can be avoided thus increasing the value of the leather.</p> <p>UNIPEL® EB is deposited in the empty parts of the skin, and between the grain and the reticular layer. Additional reactive groups are in those parts of the skin where the fiber density is low.</p>
Use guideline:	Especially for shoe upper types it is recommended to use 2 – 5 % of the UNIPEL® EB in fresh bath (50% - 65°C), for 10 – 20 min. just followed by the normal fatliquor mixture to achieve a full, round and tight grain.
Storage:	We recommend keeping the product sealed in the original package, in a clean and controlled environment, avoiding extreme temperatures.



Package: 30 Kg plastic bags in 1.050 Kg pallets.